



- Clasa de rezistența la compresiune	C30/37
- Clasele de expunere (min)	XC4+XD1+XF4
- Dozaj minim de ciment (min)	340 kg/mc
- Tip ciment conf. SR EN 197-1:2011	CEM I: SRI; I-A 52,5, 42,5; CEM II: A/B-S, HIIA-S, A-LL
- Raport apă/ciment (max)	0.5

- Clasa de rezistența la compresiune	C25/30
- Clasele de expunere (min)	XF2
- Dozaj minim de ciment (min)	300 kg/mc
- Tip ciment conf. SR EN 197-1:2011	CEM I, SRI; I-A 52,5, 42,5; CEM II: A/B-S, HIIA-S, A-L
- Raport apă/ciment (max)	0,55a

- Clasa de rezistența la compresiune	C25/30
- Clasele de expunere (min)	XF1
- Dozaj minim de ciment (min)	300 kg/mc
- Tip ciment conf. SR EN 197-1:2011	CEM I: SRI; I-A 52.5, 42.5; CEM II: A/B-S, IIIA-S, A-L;
- Raport apă/ciment (max)	0.5

- Clasa de rezistentă la compresiune	C16/20
- Clasele de expunere (min)	XC2
- Dozaj minim de ciment (min)	260 kg/mc
- Tip ciment conf. SR EN 197-1:2011	CEM I; SRI; I-A 52,5, 42,5
	CEM II; A/B-S, III-A-S, A-
- Raport apa/ciment (max)	0.60